

Product Description

ExoAir® 110AT is a 22-mil composite impermeable membrane that is comprised of 16 mils of butyl and 6 mils of HDPP facer. It can be used as the membrane, detailing accessory, as well as thru-wall flashing of an air barrier system. ExoAir 110AT when installed properly as a system will provide the requirements of an air barrier: air impermeable, continuity, structural integrity and durability.

Basic Uses

ExoAir 110AT is an impermeable, self-adhered sheet designed to be applied to exterior cavity walls in order to mitigate air infiltration/exfiltration, vapor transmission and water penetration. Typically applied to exterior sheathing boards and concrete block, ExoAir 110AT can also be applied to poured concrete, steel and wood based substrate as well as serve as detailing or a transition membrane into window and door openings. ExoAir 110AT is designed to be installed when both the air and surface temperature are 20 °F (-6 °C) and rising.

Features and Benefits

- The high-performance butyl has been tested and is compatible with the ExoAir product line.
- Primerless application allows for faster installation time.
- Manufactured to a preset, uniform thickness that provides consistent and uniform coverage.
- Rugged HDPP film protects high-performance butyl membrane against incidental damage during construction process.
- Variety of widths available for job specific needs.
- White facer reduces heat absorption, resulting in thermal stability during construction cycle.
- Material installation and service temperatures eliminate the need for low temperature or high temperature accessories.
- Reduced material weight compared to traditional 40-mil systems reduces fatigue on installers and can increase productivity.

Availability

EXOAIR® 110 AT is immediately available from your local Tremco Sales Representative or Distributor. For Distributor locations, visit www.tremcosealants.com

Coverage Rates

Varies depending on width selected

Packaging

Length: 75' (22 M)
Width: 4" (10 cm)-12 rolls/box, 6" (15 cm)-8 rolls/box,
9" (22 cm)-4 rolls/box, 12" (30 cm)-4 rolls/box,
18" (45 cm)-1 roll/box, 24" (61 cm)-1 roll/box,
36" (91 cm)-1 roll/box

Colors

White HDPP facer with green ExoAir logo.

Storage

Store ExoAir 110AT in the original, undamaged packaging in a clean, dry, and protected location where temperatures do not exceed 100 °F (37 °C).

Applicable Standards

- ExoAir 110AT has been tested to the following industry standards and test methods for air barriers:
- AATCC 127-2008 Water Resistance: Hydrostatic Pressure Test for 5 hr
- ASTM C1305 Standard Test Method for Crack Bridging Ability of Liquid-Applied Waterproofing Membrane
- ASTM D412 Standard Test Methods for Vulcanized Rubber and Thermoplastic Elastomers - Tension
- ASTM D870 Standard Practice for Testing Water Resistance of Coatings Using Water Immersion
- ASTM D882 Standard Test Method for Tensile Properties of Thin Plastic Sheeting
- ASTM D903 Standard Test Method for Peel or Stripping Strength of Adhesive Bonds
- ASTM D1876 Standard Test Method for Peel Resistance of Adhesives (T Peel Test)
- ASTM D1970 Standard Specification for Self-Adhering Polymer Modified Bituminous Sheet Materials Used as Steep Roofing Underlayment for Ice Dam Protection
- ASTM D4073 Standard Test Method for Tensile – Tear Strength of Bituminous Roofing Membranes
- ASTM D4541 Standard Test Method for Pull-Off Strength of Coatings Using Portable Adhesion Testers
- ASTM E96 Standard Test Methods for Water Vapor Transmission of Materials
- ASTM E154 Standard Test Methods for Water Vapor Retarders used in Contact with Under Concrete Slabs, on Walls or as Ground Cover - Section 10 only
- ASTM E331 Standard Test Method for Water Penetration of Exterior Windows, Skylights, Doors, and Curtain Walls by Uniform Static Air Pressure Difference
- ASTM E2178 Standard Test Method for Air Permeance of Building Materials
- ASTM E2357 Standard Test Methods for Determining Air Leakage of Air Barrier Assemblies
- NFPA 285 Standard Fire Test Method for Evaluation of Fire Propagation Characteristics of Exterior Non-Load-Bearing Wall Assemblies Containing Combustible Components.

Fire Rated Systems

EXOAIR® 110 AT has been tested in assemblies according to NFPA 285 Standard Fire Test Method for Evaluation of Fire Propagation Characteristics of Exterior Non-Load-Bearing Wall Assemblies Containing Combustible Components. All of the NFPA 285 UL listed assemblies using Tremco materials can be found using the technical bulletin: ASHRA 90.1 & NFPA 285: Defining & Specifying to Meet IECC & IBC or utilizing the following link: http://database.ul.com/cgi-bin/XYV/template/LISEXT/1FRAME/showpage.html?name=FWFX.R27656&ccnshorttitle=Exterior+Wall+System+Components&objid=1082999775&cfqid=1073741824&version=versionless&parent_id=1082761881&sequence=1

For NFPA 285 engineering judgment requests please go to [www.tremcosealants.com/NFPA 285 Engineering Judgment Request](http://www.tremcosealants.com/NFPA%20285%20Engineering%20Judgment%20Request) or contact Tremco Technical Service at 866-209-2404.

Limitations

- No more than 12 months of UV exposure before façade installation. If membrane is exposed for a period exceeding 12 months, contact Tremco Technical Service for additional recommendations at 866-209-2404, or visit the Technical Resources area of our website at www.tremcosealants.com and "Ask the Expert."

- Do not apply to damp, contaminated or frost-covered surfaces.
- Not to be used as a permanently exposed surface.
- Termination Mastic should not be used with ExoAir 110AT in a fully encapsulated area.

Warranty

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Products proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	DESCRIPTION
Type	Butyl sheet with white HDPP facer
Color	White HDPP facer
Solids	100%
Weight	0.17 lb/ft ² (0.83 kg/M ²)
Application	Self-Adhered
Thickness	22 mils: 16 mils butyl, 6 mils HDPP facer
Storage Temperature	Temperatures not exceeding 100 °F (37 °C)
Application Temperature	Above 20 °F (-6°C) and rising
Service Temperature	Intermittent Exposure up to 240 °F (115 °C)

PROPERTY	TEST METHOD	TYPICAL VALUES
Maximum V.O.C.	Method 310	0 g/L
Water Resistance	AATCC-127	Pass (5 hours)
Crack Bridging	ASTM C1305	Pass
Elongation	ASTM D412 Die C	650%
Tensile Strength		1570 psi
Peel or Stripping Strength	ASTM D903	
	Plywood	5.7 lbf/in
	CMU	8.0 lbf/in
	Exterior Sheathing	7.3 lbf/in
	ExoAir 110AT	9.0 lbf/in
Pliability, 180°, 1" (25 mm) mandrel @ -29 °F (-34 °C) (Low Temperature Flex)	ASTM D1970 – Section 7.6	Pass
Nail Seal ability	ASTM D1970 – Section 7.9	Pass
Tear Initiation	ASTM D4073	
	MD (Machine Direction)	24 lbf
	CMD (Cross Machine Direction)	21 lbf
Adhesion	ASTM D4541	38.7 psi
Flame Spread	ASTM E84	5
Smoke Development		10
Water Vapor Permeance	ASTM E96 Dry Cup ASTM E96 Wet Cup	0.02 US Perms 0.04 US Perms
Water Penetration	ASTM E331	Passed at 6.26 lb/ft ² (300 Pa) for 2 hours
Material Air Permeance	ASTM E2178; Free film Method @ 75 Pa	0.001 L/sm ²
Air Barrier Assembly Air Leakage	ASTM E2357	0.003 L/s·m ² @ 75 Pa
Fire Resistance of an Assembly	NFPA 285	Pass
Tensile Strength	ASTM D882	28 lbf/in
Resistance to Puncture	ASTM E154	52 lbf/in

0618/EXO110ATDS-AB



Tremco Commercial Sealants & Waterproofing

3735 Green Rd
Beachwood OH 44122
216.292.5000 / 800.321.7906

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1445 Rue de Coulomb
Boucherville QC J4B 7L8
514.521.9555