

Product Description

Tremco® 2550 Protection Board is a semi-flexible asphaltic sheet. It consists of a core made from a blend of asphalt, plasticizer and inert fillers. This core is sandwiched between two skins of an asphalt-saturated fiberglass. This composition is then molded and formed under heat and pressure into sheets.

Basic Uses

Tremco 2550 provides protection for approved waterproofing membranes during and after construction. The tough durable properties of the product make it ideally suited to withstand the shock and impact of rugged backfilling operations, as well as on-site foot traffic. It is used as a protective course for foundation walls, roof terraces, planters and tunnels.

Packaging

1/8" thick, 3' x 5', 200 / pallet 1/8" thick, 4' x 5', 150 / pallet

Limitations

- Not for use with Tremco TREMproof® 201/60 or Tremco TREMproof 250GC cold fluid-applied waterproofing membranes.

Warranty

Tremco warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Product proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	TYPICAL VALUES
Puncture Resistance at 94°C	200 psi
Indentation	Less than 0.9 mm
Density, lb / ft ³	88 lb/ft ³
Weight, lb / ft ²	0.92
Bitumen Content, % by weight	0.45
Inert Residual, % by weight	0.55
Binders, Fiberglass (both sides)	Full width inorganic nonwoven matting
Binders, % inorganic	100%
Bitumen Softening Point °C	108 °C
Anti-Stick Material	Polyethylene film
Alkali Attack	No disintegration
Binders, Tensile Strength	
Width, lb	24 lb
Length, lb	33 lb
Water Absorption, % weight increase (after 80 hours at 60 °C)	0.26%
Water Permeability (after 1 month)	No leakage, swelling or deterioration

0316/T2550DS-BG

Tremco Commercial Sealants & Waterproofing

3735 Green Rd
Beachwood OH 44122
216.292.5000 / 800.321.7906

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1445 Rue de Coulomb
Boucherville QC J4B 7L8
514.521.9555

