

### Product Description

Vulkem® 360NF/950NF/951NF is a modified polyurethane traffic deck coating system composed of a base coat (360NF), heavy duty intermediate coat (950NF) and a top coat (951NF). This unique waterproofing system is designed to have tenacious adhesion, extreme impact and abrasion resistance along with remarkable chemical stability. The elastomeric properties of the system's components enable the complete assembly to give and work with the concrete slab, bridging the shrinkage cracks.

Vulkem 360NF Base Coat is a low odor, low VOC, water-cured, rapid setting urethane membrane that bonds firmly to clean, dry concrete and metal. It retains its integrity even if substrate movement causes hair-line cracks of up to 1/16" (1.5 mm). If cut or damaged, Vulkem 360NF will prevent water migration between itself and the substrate.

Vulkem 950NF Intermediate Coat is a low VOC, two-component urethane that is applied after the Vulkem 360NF Base Coat has cured. The intermediate coat is loaded with aggregate to give the system excellent impact, abrasion and chemical resistance.

Vulkem 951NF Top Coat is an aliphatic, low VOC, two-component polyurethane that is applied after the Vulkem 950NF intermediate coat has cured. Interlaminar adhesion to Vulkem 950NF is exceedingly strong. The top coat affords excellent abrasion resistance, UV stability and chemical resistance to complete this Vulkem Traffic Deck Coating System.

### Basic Uses

Vulkem 360NF/950NF/951NF is a cold-applied traffic deck coating system designed for waterproofing concrete slabs and protecting occupied areas underneath from water damage. Additionally, the system will protect the concrete from the damaging effects of water, deicing salts, chemicals, gasoline, oils and anti-freeze.

### Features and Benefits

- Fast cure through time allows for use 24 hr after installation.
- Low odor and low level of Volatile Organic Compounds (VOC) provides for use in neighbor friendly, inhabited structures.
- Mildew and fungus resistance safeguards concrete surfaces against environmental contaminants.
- Excellent durability and UV resistance extends the useful life of vehicular systems.
- Recoatable and compatible with other Tremco sealants, which enhance waterproofing protection with full system compatibility.

### Availability

Immediately available from your local Tremco Sales Representative, Tremco distributor, or warehouse.

### Packaging


Vulkem 360NF: 5 gal (18.9 L) in a 6-gal (22.7-L) pail.

Vulkem 950NF: Total of 4.2-gal kit - Part A 3.25-gal (12.3 L) in a 5-gal (18.9-L) pail, Part B 0.95 gal (3.6 L) in a 1-gal pail.

Vulkem 951NF: Total of 4.6-gal kit - Part A 3.75 gal (14.2 L) in a 5-gal (18.9-L) pail, Part B 0.85 gal (3.2 L) in a 1-gal pail.

### Colors

Vulkem 951NF is available in Beige, Gray, Limestone, Black and Slate Gray. Made-to-order and special colors also are available upon request.



**SEALANT • WATERPROOFING  
& RESTORATION INSTITUTE**

**Issued to: Tremco Incorporated**  
**Product:** Vulkem® 951 NF Topcoat & Vulkem® 360 NF SL Basecoat

**ASTM D 412: Tensile Strength of Top Coat**  
 Vulkem® 951 NF  
 Tensile Strength: 4,729 psi;  
 Elongation: 157% Pass ✓

**ASTM D 4541: Adhesion of Base Coat**  
 Vulkem® 360 NF SL  
 Pull-off Adhesion: 391 psi Pass ✓

**ASTM D 4060: Abrasion Resistance of Top Coat**  
 Vulkem® 951 NF  
 Abrasion Resistance: 33 mgms loss  
 – mgms loss/1,000 cycles Pass ✓

**Validation Date:** 5/16/18-5/17/23  
**No. 951—3600523** Copyright © 2018

**DECK COATING VALIDATION**  
[www.swrionline.org](http://www.swrionline.org)

### Fire Rated Assemblies

- ANSI/UL790 - Standard Test Methods for Fire Tests of Roof Coverings
- CAN/ULC-S107 - Methods of Fire Tests of Roof Coverings

### Installation

Concrete shall be water-cured and attain a 4000 psi minimum compressive strength. Concrete finish shall be a light steel trowel followed by a fine-hair broom, or equivalent ICRI #2-#4 finish. Moisture content in the concrete must be lower than 4.5% as measured by a Tramex CME 4 Moisture Meter. Depending on concrete construction and job site location, additional concrete testing may be required. Please contact your local Tremco Sales or Technical Representative.

Please refer to the Vulkem 360NF/950NF/951NF Application Instructions for complete application details. The techniques involved may require modification to adjust to the jobsite conditions. Consult your Tremco Sales Representative or Tremco Technical Service for site conditions and requirements.

### Applicable Standards

- Conforms to:
- ASTM C957
  - CSA S413-14

### Limitations

- Do not apply to damp or contaminated surfaces.
- Use with adequate ventilation.

**Warranty**

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Products proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at [www.tremcosealants.com](http://www.tremcosealants.com) for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

**TYPICAL PHYSICAL PROPERTIES**

PROPERTY	TEST METHOD	VULKEM 360NF	VULKEM 950NF	VULKEM 951NF
Flash Point	Set-A-Flash	185 °F (85 °C)	200 °F (93 °C)	>200 °F (93 °C)
% Solids (by Weight)	ASTM D1353	91%	99%	80 to 85%
Drying Time @ 75 °F, 50% RH	ASTM D1640	25 mil film, 6 to 12 hr	12 mil film, 2 to 4 hr	12 mil film, 2 to 4 hr
Open to vehicular traffic		N/A	N/A	24 hr after cure
Weathering	ASTM D822	N/A	N/A (Indoor use only)	No effect
Salt Spray	ASTM B117	N/A	No effect	No effect
Viscosity	Brookfield C&P	8000 to 10000 cps	2000 cps	2500 cps
Elongation	ASTM D412	500%	100%	145%
Tensile Strength	ASTM D412	275 psi	4200 psi	4500 psi
Hardness (Shore A)	ASTM D2240	40 to 50	75 shore D	50 shore D
Adhesion (Peel Strength)	ASTM D903	Unprimed concrete, 45 pli, 100% cohesive failure	100% cohesive failure	100% cohesive failure
Adhesion (Pull-Off)	ASTM D4541	350 psi	N/A	N/A
Abrasion Resistance (1000 cycles)	ATSM D4060	N/A	70 mg	33 mg
Accelerated Aging	ASTM D573	No loss of elongation or tensile strength	No loss of elongation or tensile strength	No loss of elongation or tensile strength

\* Accelerated aging test. 1 daily cycle of UV and water spray greatly exceeds 1 day of real world exposure. Contact Tremco Technical Service or your local sales representative for more information.

**0220/360NF/950NF/951NFDS-DC**

Please refer to our website at [www.tremcosealants.com](http://www.tremcosealants.com) for the most up-to-date Product Data Sheets.



**Tremco Commercial Sealants & Waterproofing**

3735 Green Rd  
Beachwood OH 44122  
216.292.5000 / 800.321.7906

1451 Jacobson Ave  
Ashland OH 44805  
419.289.2050 / 800.321.6357

220 Wicksteed Ave  
Toronto ON M4H1G7  
416.421.3300 / 800.363.3213

1445 Rue de Coulomb  
Boucherville QC J4B 7L8  
514.521.9555